



EUROPEAN PATENT APPLICATION

Application number: 93114503.1

Int. Cl.⁵ A61L 27/00, A61K 6/033,
A61F 2/28, A61K 6/027

Date of filing: 09.09.93

Priority: 09.10.92 JP 271280/92

Date of publication of application:
13.04.94 Bulletin 94/15

Designated Contracting States:
DE FR GB

Applicant: NIKON CORPORATION
2-3, Marunouchi 3-chome
Chiyoda-ku
Tokyo(JP)

Inventor: Kaneko, Norio
35, Yoshida-machi,
Totsuka-ku
Yokohama-shi, Kanagawa-ken(JP)

Representative: Blumbach Weser Bergen
Kramer Zwirner Hoffmann Patentanwälte
Radeckestrasse 43
D-81245 München (DE)

54 Bone grafting material.

57 A bone grafting material for use in medicine is glass wool which has the mean diameter of 100 µm or less and whose composition is:

SiO ₂	40 - 62 % (w/w)
Na ₂ O	10 - 32 % (w/w)
CaO	10 - 32 % (w/w)
P ₂ O ₅	0 - 12 % (w/w)
CaF ₂	0 - 12 % (w/w)
B ₂ O ₃	0 - 20 % (w/w)

When said grafting material is used for treatment of periodontal disease, the grafting material is completely replaced by newly formed bone, wherein dental ankylosis of the grafting material to a tooth root does not occur and the newly formed bone and the tooth root are bound with a tissue like a periodontal membrane.

BACKGROUND OF THE INVENTIONField of the Invention

5 The present invention relates to a bone grafting material for use in medicine.

Related Background Art

10 Ceramics such as hydroxyapatite and tricalcium phosphate (TCP) as well as crystallized glass such as A-W ceramics have osteoconduction, and granular, porous and block materials are clinically applied as bone grafting materials for treatment of bone defect.

15 The grafting materials, which are artificial, are foreign bodies to an organism. And preferably, these materials are completely replaced by newly formed bone after the bone restoration treatment. Further, when these materials are used for treatment of periodontal disease, dental ankylosis of the grafting materials to the teeth root is preferably prevented and newly formed bone and the teeth root are preferably bound with a tissue like a periodontal membrane and cementum.

20 But, while having capacity to regenerate bone, the above-mentioned conventional grafting materials are taken in to remain in the newly formed bone, which causes undesirable dental ankylosis. Granular grafting materials may come out of the gap between gingiva and tooth root, which hinders sufficient restorative effect. And it is extremely difficult to fibrize bioactive ceramics and glass ceramics.

SUMMARY OF THE INVENTION

The object of the present invention is to solve the above-mentioned problems.

25 In order to achieve this object, the present invention is to provide a bone grafting material for use in medicine which is glass wool having the mean diameter of 100 μm or less and whose composition is:

SiO ₂	40 - 62 % (w/w)
Na ₂ O	10 - 32 % (w/w)
CaO	10 - 32 % (w/w)
P ₂ O ₅	0 - 12 % (w/w)
CaF ₂	0 - 12 % (w/w)
B ₂ O ₃	0 - 20 % (w/w)

30 35 When used in treatment of periodontal disease, the bone grafting material of the present invention is completely replaced by the newly formed bone after bone restoration treatment, wherein dental ankylosis of the grafting material to the teeth root does not occur and the newly formed bone and the teeth root are bound with the periodontal-membrane-like tissue.

40 The process in which the present invention produces such bone restorative effect has not been known yet. But, it is probable that the above-mentioned effect is produced by the osteoconduction of the bioactive glass grafting material, the stimulation given to the organism by the ions of the components of the grafting material which flow out in vivo as well as the dissolution of the glass wool grafting material which occurs in vivo during the bone restoration treatment.

45 The rate of dissolution of the glass wool can be controlled by changing the diameter of the short fibers or composition of the glass. Thus, the glass wool can be prepared according to the application thereof. In addition, the outflow of the grafting glass from the position into which it is tilted can be prevented by forming the glass as short fibers so that the effect of the bioactive glass may be fully exerted.

50 The glass according to the present invention consists of SiO₂/Na₂O/CaO/P₂O₅/CaF₂/B₂O₃, more preferably, of SiO₂/Na₂O/CaO/P₂O₅.

Na₂O may be replaced by another alkaline metal oxide (for example, K₂O, Li₂O, and so on). Part of CaO may be replaced by another alkaline earth metal oxide (for example, MgO). Further, oxides other than the essential components SiO₂, Na₂O and CaO (for example, ZrO₂, TiO₂, La₂O₃, Al₂O₃, Ta₂O₅, Nb₂O₅, and so on) and fluorides (for example, NaF, Na₂SiF₆) may be added.

55 If the diameter of the short fibers of the glass wool is too large, the grafting material becomes brittle and cannot be tilted properly. On the other hand, if the diameter is too small, the grafting material has dissolved in vivo before being replaced by the newly formed bone and proper bone restoration is not carried out. Accordingly, the mean diameter of the short fibers is preferably 1 - 100 μm , more preferably 2 -

BEST AVAILABLE COPY

50 μm , and most preferably 5-20 μm .

The effect of the bone grafting material of the present invention was verified by experiment of treatment of periodontal disease, but this bone grafting material can be applied to other bone restoration treatment. It can be filled in the gap between an artificial teeth and a bone in order to graft the artificial tooth root to the bone, and can be used for treatment of resorption of cervical bone in order to regenerate bone around an artificial tooth root. In addition, this grafting material can be used in combination with the GTR method. Thus, further effects can be expected.

The grafting material of the present invention may be prepared by the vapor spray process, the spinning process, the flame attenuation process, the rotary process, and so on. But process of preparing the grafting material of the present invention are not limited to those mentioned above.

Now an embodiments of the present invention will be described concretely, though the embodiment does not set any limit to the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

Glass wool of bioactive glass having a composition of SiO_2 (46.1 % (w/w))/ Na_2O (24.4 % (w/w)) CaO (26.9 % (w/w)) P_2O_5 (2.6 % (w/w)) were prepared so as to have the mean diameter of 2 - 50 μm .

The glass wool were filled in the periodontal disease (i.e. defect in jaw bone around a teeth) which had been experimentally formed in the jaw bone of an adult dogs. After four months, condition of the diseased part was estimated by examining pathological specimens. The result showed that the glass wool had been completely replaced by newly formed bone, that dental ankylosis of the grafting material to the tooth root had not been formed, and that the newly formed bone and the tooth root had been bound with a periodontal-membrane-like tissue.

As described above, when the bone grafting material of the present invention is used for treatment of periodontal disease, the grafting material is completely replaced by newly formed bone after bone restoration treatment, wherein dental ankylosis of the grafting material to the tooth root does not occur and the newly formed bone and the tooth root are bound with the periodontal-membrane-like tissue.

Claims

1. A bone grafting material for use in medicine which is glass wool having the mean diameter of 100 μm or less and whose composition is:

SiO_2	40 - 62 % (w/w)
Na_2O	10 - 32 % (w/w)
CaO	10 - 32 % (w/w)
P_2O_5	0 - 12 % (w/w)
CaF_2	0 - 12 % (w/w)
B_2O_3	0 - 20 % (w/w).

BEST AVAILABLE COPY



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 93 11 4503

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.S)
Y	FR-A-2 548 658 (MITSUBISHI) * page 8; example 1 * * claims 1,16,17 * ---	1	A61L27/00 A61K6/033 A61F2/28 A61K6/027
Y	EP-A-0 206 726 (UNIVERSITY OF FLORIDA) * claim 1 *	1	
Y	FR-A-2 393 020 (KULZER) * page 2, line 24 - line 30; claims 7,8 * ---	1	
A	WO-A-86 04807 (UNIVERSITY OF DAYTON) * claims 1,2 *	1	

*			
TECHNICAL FIELDS SEARCHED (Int.Cl.S)			
A61L A61K A61F			

The present search report has been drawn up for all claims			
Place of search	Date of completion of the search		Examiner
THE HAGUE	21 January 1994		Peltre, C
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document			
T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application I : document cited for other reasons & : member of the same patent family, corresponding document			

BEST AVAILABLE COPY